



CEWELD AA M37-42

TYPE	Seamless medium alloyed metal powder fluxcored wire without slag for hardfacing using Ar-CO2 Mixgas				
ANWENDUNGEN	375-450 HB, hardfacing and rebuilding alloy for wornout wheels, rails, tires, conveyors, crossings, shafts, bufferlayers prior to hardfacing. excelent wear and abrasion resistance against heavy impact and shock, machinable with carbide tools.				
EIGENSCHAFTEN	Due to the high resistance to cracking and excelent toughness, all weld metal requires no buffer layer except on materials considered critical. Suited for wear parts subject to heavy impact and shock. The interpass temperature should be maximum 250°C. The weld metal is machinable with carbide tip tools, hardening is possible. The maximum hardness is dependent on the base metal and is achieved already in the first layer.				
KLASSIFIKATION	EN ISO DIN	14700: T ZFe2 8555: MF 1-GF-40 GPS			
GEEIGNET FÜR	Conveyors and transport surfaces, tires, bucket and loader teeth, cruscher jaws, Bufferlayers, crane wheels, axis, gear parts, winches etc.				
ZULASSUNGEN					
SCHWEISSPOSITIONEN	PAPBPC				
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C 0.4	Si 0.7	Mn 1.5	Cr 2.5	Mo 0.5
MECHANISCHE GÜTEWERTE	Heat Treatment As Welded	R _{p0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 40 HRc
RÜCKTROCKNUNG	Not required				
GAS ACC. EN ISO 14175	M21				



CEWELD AA M37-42

AA M37-42 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663423214

AA M37-42 1,6MM

Packaging	KG/unit	EanCode
K-300	15	8720663423221