



CEWELD FL 8111

TYPE	Fluoride basic agglomerated flux for stainless steel SAW welding.			
ANWENDUNGEN	Sub arc flux suitable for a wide range off applications in offshore and general steelwork, cladding valves, shafts, tanks, steel mill rollers etc.			
EIGENSCHAFTEN	FL 8111 is a fluoride basic agglomerated flux for stainless steel SAW welding. Basicity: about 2,6 (according to Boniszewski) Current: DC or AC, in single or multi-wires. Grain size: 2-28			
KLASSIFIKATION	EN ISO	14174: SA FB 2 65 AC H5		
GEEIGNET FÜR	Submerged arc welding with stainless steel wires, AISI 410, 410NiMo, 308L, 316L, 2209 duplex, 347, 309L, 309LMo, 308H, super duplex, zeron 100, SAF 2507			
ZULASSUNGEN				
SCHWEISSPOSITIONEN				
TYPISCHE CHEMISCHE ZUSAMMENSETZUNG NACH GEWICHT (%)	CaO+MgO	SiO2	Al2O3	CaF2
	35	20	25	15
MECHANISCHE GÜTEWERTE				
RÜCKTROCKNUNG	Not required			
GAS ACC. EN ISO 14175				



CEWELD FL 8111

FL 8111 0,2 - 2,8MM

Packaging	KG/unit	EanCode
Bag	25	8720663404121