



CEWELD AA B Corten

TYPE	seamless basic slag flux cored wire for M21							
ANWENDUNGEN	Bridge-, general steel construction. Onshore and Offshore. General engineering. Heavy transportation and rail construction, etc.							
EIGENSCHAFTEN	AA B Corten is a seamless basic flux cored wire have a excellent weld puddle. This wire offers a unique welding deposit with more than 1% nickel and 0,5% Cu due to the seamless production process the hydrogen content is below HD<3ml/100g weld metal even after long storage.							
KLASSIFIKATION	AWS A 5.29: E81T1-Ni1M-J H4							
GEEIGNET FÜR	CuNi, Reh ≤ 460MPa ISO 15608: 1.4 1.1845, 1.8946, 1.8958, 1.1861, 1.8963,, 1.8965, 1.1866, 1.1867, 1.1869, S235JRG2Cu, S235J2G4Cu, S235J0Cu, S235JRW, S355J0Cu, S355J2G3Cu, S355J0W, 235J2W- S355J2W, S355K2W, WTSt 37, WTSt 52, Fe 360 C KI, Fe 360 D KI, Fe 510 C 1 KI, Fe 510 D 1 KI, Fe 510 C 2 KI, Fe 510 D 2 KI ASTM A 588M Grade A,B, K, A 618 Gr. II; A 709 Gr. 50 WF3, A 242 Type 1 CORten A, B, C, Patinax 37, Weathering, DOCOL 355 W, DOMEX 355 W, Allwesta, DIWETEN...							
ZULASSUNGEN	CE							
SCHWEISSPOSITIONEN	  							
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Cu
	0.05	0.7	1.5	0.015	0.015	0.5	1.1	0.5
MECHANISCHE GÜTEWERTE	Heat Treatment	RP0,2 (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardnes	
					-40°C			
	As Welded	500	620	22	70		HRc	
RÜCKTROCKNUNG	Not required							
GAS ACC. EN ISO 14175	M21							