

CEWELD AIMg 5

TYPE Mig filler metal for welding Aluminium Magnesium alloys.

ANWENDUNGEN Filler metal for welding Aluminium alloys with maximum 5% Magnesium. This Magnesium alloyed Aluminium wire, thanks to its excellent corrosion resistance and its high mechanical properties is mainly used in ship yards, car and railway industry. Thicker sections should be preheated (150°C) prior to welding.

EIGENSCHAFTEN Excellent weldability and good mechanical strength combined with good corrosion resistance are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AIMg5 is one of the most popular types within the range of aluminum alloys and covers a weight range of alloys.

KLASSIFIKATION

AWS	A 5.10: ER5356
EN ISO	18273: S Al 5356 (AlMg5Cr(A))
W.Nr.	3.3556
F-nr	22

GEEIGNET FÜR **Aluminium alloys:**
 AlMg3, AlMg4, AlMg5, AlMgSi1, AlMgSi0,5, AlMgMn, AlZnMg1, G-AlMg3Si, G-AlMg5Si, G-AlMg10, AlMg1SiCu, AlMgSi0,7, AlZn4,5Mg1, AlZnMg4,5Mn, AlZn5,5Mg1, AlSi1MgMn, AlSiMg(A), AlMg 1 3.3315, 3.3545, 3.3206, 3.3210, 3.3215, 3.3211, 3.4335, 3.3535, 3.3555, EN AW 5086, EN AW 6060, EN AW 6005A, EN AW , EN AW 6061, EN AW 7020, EN AC 51400, EN AC 51300, EN AC 51100, EN AW 5454

ZULASSUNGEN CE


SCHWEISSPOSITIONEN

Si	Mn	Cr	Ti	Al	Mg
0.2	0.1	0.1	0.1	Rem.	5

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	130	280	25	HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD ALMG 5

ALMG 5 0,8MM

Packaging	KG/unit	EanCode
D-100	0,5	8720663406866
D-200	2	8720663406873
D-300	6	8720663406859

ALMG 5 1,0MM

Packaging	KG/unit	EanCode
D-100	0,5	8720663406903
D-200	2	8720663406910
D-300	7	8720663406897
Drum	80	8720663406880

ALMG 5 1,2MM

Packaging	KG/unit	EanCode
D-100	0,5	8720663406927
D-200	2	8720663406934
D-300	7	8720663406989

ALMG 5 1,6MM

Packaging	KG/unit	EanCode
D-300	7	8720663406941

ALMG 5 2,0MM

Packaging	KG/unit	EanCode
BS-300	7	8720663406958

ALMG 5 2,4MM

Packaging	KG/unit	EanCode
D-300	7	8720663406965