



CEWELD ER 383 Tig

TYPE	ER 383 stainless steel Tig wire for GTAW welding									
ANWENDUNGEN	Tanks and process vessels, Piping systems, agitators, rotors, cast pumps and valves for use in the fertilizer, phosphoric, sulphuric and acetic acid plants									
EIGENSCHAFTEN	ER 383 is used to weld base metals of similar composition to itself or to other grades of stainless steel. ER383 contains a low maximum of carbon, silicon, and sulfur to decrease the hot cracking and fissuring, while maintaining the resistance to corrosion.									
KLASSIFIKATION	AWS	A 5.9: ER383								
	EN ISO	14343-A: W 27 31 4 Cu L								
	W.Nr.	1.4563								
	F-nr	6								
	FM	5								
GEEIGNET FÜR	Alloy 825 N08825 , Alloy 825 h Mo N08821, Alloy 28 and Alloy 20 (X1NiCrMoCu31-27-4), Alloy 904L (X1NiCrMoCu25-20-5), 1.4563, 1.4539, NiCr 21 Mo 2.4858, NiCr 21 Mo 6Cu 2.6410, X3NiCrCuMoTi27-23 1.4503									
ZULASSUNGEN	CE									
SCHWEISSPOSITIONEN										
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu
	0.02	0.4	1.55	0.017	0.01	28.2	32.1	3.9	0.05	0.95
MECHANISCHE GÜTEWERTE	Heat Treatment			R _{P0,2} (MPa)		R _m (MPa)		A ₅ (%)		Hardness
	As Welded			380		570		38		HRc
RÜCKTROCKNUNG	Not required									
GAS ACC. EN ISO 14175	I1, I3									



CEWELD ER 383 Tig

ER 383 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720682050088