

CEWELD S-SnAg5

TYPE	6% silver containing cadmium free soft solder alloy
ANWENDUNGEN	- Copper pipe installation - Refrigeration and air-conditioning technology - Soft soldering of stainless steel - Also suitable for extreme cryogenic temperatures even up to -196 °C
EIGENSCHAFTEN	Alloy: Sn94Ag6 / Solidus: 221°C / Liquidus: 279°C / Deposit color: Silver / Shear Strength (copper lap joint): 10,600 PSI
KLASSIFIKATION	
GEEIGNET FÜR	Copper, stainless steel
ZULASSUNGEN	
SCHWEISSPOSITIONEN	      
MECHANISCHE GÜTEWERTE	
RÜCKTROCKNUNG	Not required
GAS ACC. EN ISO 14175	