



CEWELD 4130

TYPE	High strength low alloyed Chromium / Molybdenum filler metal.
APPLICATIONS	Used in aeronautical sector, construction of connecting rods for automotive sector, fixing part, gears, bolts, axes etc..
PROPERTIES	4130 offers extreme high strength with excellent ductility and good weldability. Preheat and interpass temperature > 200°C

CLASSIFICATION W.Nr. 1.7218

SUITABLE FOR 1.7218, 1.7225
25 CD4, 13 CD45, 16MnCr5, 25CrMo4, 42CrMo4
AISI 4130, 8630, 4140

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL
ANALYSIS OF THE FILLER
METAL (%)

C	Mn	Si	Cr	Mo	Ni
0.3	0.5	0.3	1	0.2	0.1

MECHANICAL PROPERTIES

Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	1140	1170	11	38 HRc

REDRYING Not required

GAS ACC. EN ISO 14175