



CEWELD AA 410 NiMo

TYPE	Flux cored CrNiMo alloyed welding wire for rebuilding and cladding							
APPLICATIONS	Continuous casting rolls, centrifuges, valves, Pelton- and Francis- turbines							
PROPRIÉTÉS	Hardfacing alloy for cladding steel mill rollers, thermoshock resistant and suitable for Francis and Pelton turbines. Used in steam power plants for its excelent resistance to cavitation and stress corrosion cracking.CEWELD® AA 410NiMo is a Cr-Ni-Mo- alloyed, gas-shielded flux-cored wire electrode for cladding. The corrosion resistant deposit offers a medium hardness and is resistant against metal-metal wear and high surface pressure.							
CLASSIFICATION	AWS A 5.22: E410NiMoT0-4 EN ISO 14700: T Fe7, 17633-A: T 13 4 M M21 2 / T 410NiMo							
CONVIENT POUR	13%Cr - 4%Ni - 0,5%Mo Steel 1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414, GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13 ACI Gr. CA 6 NM							
AGRÉMENTS								
POSITIONS DE SOUDAGE	 PA  PB  PC							
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	P	Cr	Ni	Mo	Fe
	0.05	0.9	0.9	0.015	13.5	4.5	0.7	Rem.
PROPRIÉTÉS MÉCANIQUES	Heat Treatment		R _{p0,2} (MPa)		R _m (MPa)		A5 (%)	Hardness
	As Welded				>760		>35	40 HRc
ETUVAGE	Not required							
GAS ACC. EN ISO 14175	M21							



CEWELD AA 410 NiMo

AA 410 NIMO 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411761

AA 410 NIMO 2,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411815

AA 410 NIMO 2,4MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411822