



CEWELD AA 310B

TYPE	Basic flux cored stainless steel welding wire for M21 and M20 gas				
APPLICATIONS	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers Especially where rutile flux cored wire gives a to high risk for cracking this basic type is a better choice				
PROPRIÉTÉS	For welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. AA 310B has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309L				
CLASSIFICATION	AWS	A 5.22: E310T0-4			
	EN ISO	17633-A: T 25 20 B M21 3			
	W.Nr.	1.4842			
	F-nr	6			
	FM	5			
CONVIENT POUR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835,1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21, GX40CrNiSi22-10, X15CrNiSi20-12, 310, 310S, CK20, 305, 314, 725LN, 316L ASTM A297 HF / A297HJ UNS: S31000, S31008, S31050, S31603				
AGRÉMENTS	CE				
POSITIONS DE SOUDAGE	  				
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	Cr	Ni
	0.1	0.5	2.5	25.5	21
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V RT Hardness
	As Welded	400	590	30	80 HRc
ETUVAGE	Not required				
GAS ACC. EN ISO 14175	M20, M21				