



CEWELD ERTi-7

TYPE Titanium Tig welding wire grade 7

APPLICATIONS Grade 7 is often used in the aerospace industry because of its favorable weight/strength ratio. Also, in petrochemical, pharmaceutical, heat exchangers, pipes and valves.

PROPRIÉTÉS Grade 7 has better corrosion resistance than grade 2 due to the addition of 0.12-0.25% palladium, mechanical properties are similar to grade 2. The deposit is ductile and provides excellent corrosion resistance in oxidizing environments. The unique combination of mechanical strength and corrosion resistance makes the alloy a preferred choice in many applications to prevent or solve problems. The wire is cleaned in a very special way to provide a porous and ductile weld deposit.

CLASSIFICATION

AWS	A 5.16: ERTi-7
EN ISO	24034: S Ti 2401 / TiPd0,2A
F-nr	51

CONVIENT POUR Titanium grade 7, Grade 2, Grade 16
Alloy group 24 (2401, 2403, 2405)

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL
D'APPORT (%)**

C	H	O	Fe	Pd	Ti
0.02	0.005	0.1	0.1	0.2	Rem.

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	275	345	20	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 I1



CEWELD ERTi-7

ERTI-7 1,0MM

Packaging	KG/unit	EanCode
D-300	10	8720663406613

ERTI-7 1,2MM

Packaging	KG/unit	EanCode
D-300	10	8720663406590