



CEWELD Alloy 230 Tig

TYPE Nickel based Tig filler metal for welding similar NiCrW alloys.

TOEPASSINGEN In the chemical process industry, CEWELD® Alloy 230 is used for catalyst grid supports in ammonia burners, high-strength thermocouple protection tubes, high-temperature heat exchangers, ducts, high-temperature bellows, and various other key process internals. In the industrial heating industry, applications for 230 alloy include furnace retorts, chains and fixtures, burner flame shrouds, recuperator internals, dampers, nitriding furnace internals, heat-treating baskets, grates, trays, sparger tubes, thermocouple protection tubes, cyclone internals, and many more.

EIGENSCHAPPEN CEWELD® Alloy 230 combines properties which make it ideally suited for a wide variety of component applications in the aerospace and power industries. It is used for combustion cans, transition ducts, flame holders, thermocouple sheaths, and other important gas turbine components.

CLASSIFICATIE

AWS	A 5.14: ERNiCrWMo-1
EN ISO	18274: S Ni 6231(NiCr22W14Mo2)
W.Nr.	2.4733
F-nr	43
FM	6

GESCHIKT VOOR **UNS-Nummer: N06230**
 Haynes Alloy 230,
 ASTM: B435, B564, B572, B619, B622, B626, B366, 5981
 AMS: 5878, 5839
 Haynes 25 alloy

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	Cr	Ni	Mo	W	Co	Al
0.1	0.4	0.5	22	57	2	14	4	0.3

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	490	780	48	HRc

HERDROGEN Not required

CURRENT TYPE: DC-

GAS ACC. EN ISO 14175 I1



CEWELD Alloy 230 Tig

ALLOY 230 TIG 1,6 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720682051399
ALLOY 230 TIG 2,0 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663424235
ALLOY 230 TIG 2,4 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663420152